



Amplus

PC12 1010 BK

Polycarbonate General Purpose Black

Physical	Units	English System	Metric System	Comments (ASTM)
Melt Flow	g/10 min	10	10	D1238
Reinforcement/Filler	% (ash)	0	0	D2584
Density	lb/in ³ (gr/cc)	1.2	1.2	D792
Mechanical				
Tensile Strength @ Break	psi (Mpa)	8200	57	D638
Tensile Elongation @ Break	%	80	80	D638
Flexural Strength	psi (Mpa)	11500	79	D790
Flexural Modulus	psi (Mpa)	300000	2069	D790
Izod Impact Strength	ft lbs/in (j/m)	10	534	D256
Processing Information				
Melt Temperatures	F (°C)	480-580	240-300	
Mold Temperatures	F (°C)	120-220	50-100	

All values displayed on this information sheet are results of data gathered during a conditioned controlled laboratory testing. Laboratory conditions and production condition differences should be taken into consideration when designing parts and/or tooling and/or any other design criteria. Vidal Plastics does not guarantee the accuracy of this information nor the impact of this information during regular processing and production of parts and pieces.

Vidal Plastics, LLC - 616 N Norman Ave - Evansville, IN - 47711
 ph. 812-492-4330 / fax 812-645-3868 / info@vidalplastics.com