



Siccus

PA6-2 GR33 22 BK

Nylon 6 Utility 33% Glass Reinforced Black

Physical	Units	English System	Metric System	Comments (ASTM)
Melt Flow	g/10 min	N/A	N/A	D1238
Reinforcement/Filler	% (ash)	33	33	D2584
Density	lb/in ³ (gr/cc)	1.38	1.38	D792
Mechanical				
Tensile Strength	psi (Mpa)	22,000	152	D638
Tensile Elongation	%	3	3	D638
Flexural Strength	psi (Mpa)	32,000	221	D790
Flexural Modulus	psi (Mpa)	1,400,000	9653	D790
Izod Impact Strength	ft lbs/in (j/m)	2.0	107	D256
Processing Information				
Drying Time @ 180 °F	Hrs	2-4	2-4	
Max Moisture	%	0.12	0.12	
Melt Temperatures	F (°C)	480 - 540	245 - 280	
Mold Temperatures	F (°C)	480 - 540	245 - 280	

All values displayed on this information sheet are results of data gathered during a conditioned controlled laboratory testing. Laboratory conditions and production condition differences should be taken into consideration when designing parts and/or tooling and/or any other design criteria. Vidal Plastics does not guarantee the accuracy of this information nor the impact of this information during regular processing and production of parts and pieces.

Vidal Plastics, LLC - 616 N Norman Ave - Evansville, IN - 47711
 ph. 812-492-4330 / fax 812-645-3868 / info@vidalplastics.com